

TABLE 1: Cactus Project Drill Assays (Aug 27, 2025)

HoleID	Zone	From	To	Length	From	To	Length	Total Cu	Cu Tsol	Mo
		Feet			Meters			Grade (%)		
ECM-291	unbound	596.0	623.8	27.8	181.7	190.1	8.5	0.42	0.27	0.001
	oxide	674.7	750.7	76.0	205.6	228.8	23.2	0.57	0.51	0.002
	enriched	1047.0	1067.0	20.0	319.1	325.2	6.1	0.22	0.21	0.013
	enriched	1207.0	1257.0	50.0	367.9	383.1	15.2	0.84	0.83	0.041
	enriched	1356.0	1465.0	109.0	413.3	446.5	33.2	1.62	1.42	0.035
	including	1366.0	1396.0	30.0	416.4	425.5	9.1	2.97	2.96	0.044
	primary	1465.0	2154.7	689.7	446.5	656.8	210.2	0.45	0.03	0.009
ECM-293	enriched	721.4	796.0	74.6	219.9	242.6	22.7	0.45	0.44	0.003
	enriched	894.3	1227.5	333.2	272.6	374.1	101.6	1.16	0.96	0.007
	including	985.0	1005.0	20.0	300.2	306.3	6.1	1.84	1.80	0.008
	primary	1227.5	1942.3	714.8	374.1	592.0	217.9	0.63	0.04	0.015
	including	1327.0	1487.0	160.0	404.5	453.2	48.8	0.97	0.06	0.029
ECM-295	oxide	611.8	642.5	30.7	186.5	195.8	9.4	0.25	0.17	0.002
	including	681.7	731.9	50.2	207.8	223.1	15.3	0.34	0.31	0.002
	enriched	681.7	804.0	122.3	207.8	245.1	37.3	0.21	0.19	0.002
	enriched	905.0	985.1	80.1	275.8	300.3	24.4	0.21	0.20	0.002
	primary	1216.8	1347.0	130.2	370.9	410.6	39.7	0.12	0.02	0.002
	primary	1397.0	1441.4	44.4	425.8	439.3	13.5	0.17	0.02	0.003
ECM-296	enriched	1147.7	1198.0	50.3	349.8	365.2	15.3	0.89	0.88	0.003
	enriched	1251.4	1464.0	212.6	381.4	446.2	64.8	1.39	1.29	0.025
	including	1341.0	1371.0	30.0	408.7	417.9	9.1	2.27	2.18	0.08
	primary	1464.0	1722.9	258.9	446.2	525.1	78.9	0.17	0.06	0.003
ECM-298	enriched	337.5	388.2	50.7	102.9	118.3	15.5	0.50	0.49	0.001
	enriched	417.4	500.0	82.6	127.2	152.4	25.2	0.33	0.32	0.001
	enriched	855.7	896.0	40.3	260.8	273.1	12.3	0.13	0.09	0.001
	enriched	966.0	997.0	31.0	294.4	303.9	9.4	0.10	0.04	0.001
	primary	1057.0	1077.0	20.0	322.2	328.3	6.1	0.13	0.04	0.001
	primary	1107.0	1260.0	153.0	337.4	384.0	46.6	0.12	0.03	0.001
	primary	1352.0	1388.0	36.0	412.1	423.1	11.0	0.11	0.01	0.001
ECM-304	enriched	735.0	960.0	225.0	224.0	292.6	68.6	0.23	0.20	0.002
	including	772.8	810.7	37.9	235.5	247.1	11.6	0.58	0.54	0.002
	primary	960.0	1027.0	67.0	292.6	313.0	20.4	0.13	0.03	0.001
ECM-306	enriched	1077.0	1189.8	112.8	328.3	362.7	34.4	0.36	0.34	0.001
	including	1137.0	1157.0	20.0	346.6	352.7	6.1	0.72	0.65	0.001
ECM-307	unbound	247.0	996.9	52.0	75.3	303.9	15.8	0.21	0.18	0.001
	enriched	547.0	577.0	30.0	166.7	175.9	9.1	0.18	0.04	0.001
	oxide	735.0	952.5	217.5	224.0	290.3	66.3	0.36	0.29	0.002
	including	755.0	775.0	20.0	230.1	236.2	6.1	0.69	0.54	0.001
ECM-308	enriched	723.5	926.0	202.5	220.5	282.2	61.7	0.37	0.36	0.003
	including	734.0	808.0	74.0	223.7	246.3	22.6	0.69	0.68	0.003
	enriched	1116.0	1146.0	30.0	340.2	349.3	9.1	0.20	0.19	0.001

	enriched	1375.7	1433.0	57.3	419.3	436.8	17.5	0.28	0.14	0.001
ECM-310	enriched	317.0	337.0	20.0	96.6	102.7	6.1	0.26	0.22	0.001
	oxide	441.5	475.3	33.8	134.6	144.9	10.3	0.84	0.69	0.001
	enriched	536.6	583.0	46.4	163.6	177.7	14.1	0.81	0.78	0.001
	primary	593.0	783.7	190.7	180.7	238.9	58.1	0.46	0.04	0.013
	including	657.0	717.0	60.0	200.3	218.5	18.3	0.91	0.05	0.034
ECM-311	including	740.0	760.0	20.0	225.6	231.6	6.1	0.83	0.83	0.002
	enriched	740.0	800.0	60.0	225.6	243.8	18.3	0.38	0.38	0.001
	primary	838.0	858.0	20.0	255.4	261.5	6.1	0.17	0.03	0.001
	primary	888.0	1169.2	281.2	270.7	356.4	85.7	0.14	0.02	0.001
ECM-320	enriched	763.0	969.0	206.0	232.6	295.4	62.8	0.34	0.33	0.001
	including	869.0	889.0	20.0	264.9	271.0	6.1	0.63	0.61	0.001
	primary	1077.0	1169.0	92.0	328.3	356.3	28.0	0.17	0.02	0.001
	including	1109.0	1129.0	20.0	338.0	344.1	6.1	0.32	0.03	0.001
	including	1199.0	1219.0	20.0	365.5	371.6	6.1	0.18	0.02	0.001
	primary	1199.0	1269.0	70.0	365.5	386.8	21.3	0.11	0.02	0.001
ECM-323	enriched	598.0	782.0	184.0	182.3	238.4	56.1	0.31	0.29	0.002
	including	614.8	635.0	20.2	187.4	193.5	6.2	0.68	0.66	0.002
	enriched	822.0	923.2	101.2	250.5	281.4	30.8	0.16	0.15	0.001
	primary	963.0	1119.0	156.0	293.5	341.1	47.5	0.12	0.02	0.001
	primary	1149.0	1274.5	125.5	350.2	388.5	38.3	0.11	0.01	0.002
ECM-325	oxide	771.0	791.0	20.0	235.0	241.1	6.1	0.11	0.10	0.001
	enriched	984.5	1066.2	81.7	300.1	325.0	24.9	0.15	0.14	0.001
	enriched	1163.5	1257.2	93.7	354.6	383.2	28.6	0.33	0.32	0.001
ECM-328	oxide	977.0	1037.0	60.0	297.8	316.1	18.3	0.20	0.13	0.001
	enriched	1037.0	1325.0	288.0	316.1	403.9	87.8	0.24	0.21	0.001
	including	1069.0	1089.0	20.0	325.8	331.9	6.1	0.46	0.44	0.001
ECM-330	oxide	336.8	394.7	57.9	102.7	120.3	17.6	0.23	0.21	0.003
	enriched	466.0	708.0	242.0	142.0	215.8	73.8	0.41	0.40	0.002
	including	484.9	533.5	48.6	147.8	162.6	14.8	0.68	0.66	0.001
	enriched	748.6	818.0	69.4	228.2	249.3	21.2	0.24	0.23	0.002
	enriched	848.0	1101.4	253.4	258.5	335.7	77.2	0.21	0.18	0.002
	including	868.0	903.2	35.2	264.6	275.3	10.7	0.36	0.35	0.002
	primary	1207.0	1227.0	20.0	367.9	374.0	6.1	0.14	0.11	0.003
	primary	1267.0	1297.0	30.0	386.2	395.3	9.1	0.16	0.02	0.006
	primary	1357.0	1644.1	287.1	413.6	501.1	87.5	0.28	0.02	0.01
	including	1437.0	1457.0	20.0	438.0	444.1	6.1	0.48	0.03	0.022
ECM-331	no significant intercepts					0.0				
ECM-332	oxide	326.3	376.0	49.7	99.5	114.6	15.1	0.27	0.19	0.001
	enriched	396.0	448.3	52.3	120.7	136.6	15.9	0.22	0.21	0.001
	enriched	478.0	608.3	52.5	145.7	185.4	16.0	0.15	0.13	0.004
	enriched	653.0	737.0	84.0	199.0	224.6	25.6	0.78	0.76	0.01
	including	704.5	727.0	22.5	214.7	221.6	6.9	1.67	1.65	0.011
	enriched	767.3	845.2	77.9	233.9	257.6	23.7	0.59	0.57	0.005

ECM-333	enriched	1147.0	1287.5	140.5	349.6	392.4	42.8	0.81	0.58	0.012
	primary	1287.5	1604.0	316.5	392.4	488.9	96.5	0.25	0.03	0.007
	including	1307.0	1377.0	70.0	398.4	419.7	21.3	0.43	0.04	0.009
	primary	1657.0	1859.0	202.0	505.1	566.6	61.6	0.21	0.02	0.024
ECM-334	enriched	604.0	796.0	192.0	184.1	242.6	58.5	0.23	0.21	0.001
	enriched	888.0	948.0	60.0	270.7	289.0	18.3	0.11	0.11	0.002
	enriched	1063.2	1161.3	98.1	324.1	354.0	29.9	0.11	0.10	0.002
	primary	1340.0	1475.0	135.0	408.4	449.6	41.1	0.12	0.02	0.002
	primary	1575.0	1599.0	24.0	480.1	487.4	7.3	0.11	0.01	0.002
ECM-336	oxide	622.6	687.2	64.6	189.8	209.5	19.7	0.61	0.59	0.01
	including	667.0	687.2	20.2	203.3	209.5	6.2	1.52	1.50	0.015
	enriched	749.5	1068.0	318.5	228.4	325.5	97.1	0.54	0.51	0.01
	including	819.0	839.0	20.0	249.6	255.7	6.1	1.05	1.03	0.009
	enriched	1098.0	1278.0	180.0	334.7	389.5	54.9	1.34	0.94	0.043
	including	1132.1	1157.0	24.9	345.1	352.7	7.6	4.85	4.74	0.035
	including	1278.0	1442.7	164.7	389.5	439.7	50.2	0.58	0.04	0.012
	primary	1278.0	2076.1	798.1	389.5	632.8	243.3	0.33	0.02	0.005
ECM-337	oxide	576.0	602.0	26.0	175.6	183.5	7.9	0.23	0.14	0.002
	enriched	644.6	746.0	101.4	196.5	227.4	30.9	0.32	0.31	0.002
	enriched	1030.0	1050.0	20.0	313.9	320.0	6.1	0.11	0.10	0.001
	enriched	1086.0	1106.6	20.6	331.0	337.3	6.3	0.23	0.21	0.002
	primary	1667.0	1748.0	81.0	508.1	532.8	24.7	0.12	0.02	0.003
ECM-338	enriched	294.8	327.0	32.2	89.9	99.7	9.8	0.15	0.11	0.001
	enriched	495.1	548.0	52.9	150.9	167.0	16.1	0.57	0.54	0.001
	primary	558.0	660.0	102.0	170.1	201.2	31.1	0.48	0.03	0.004
ECM-339	enriched	564.3	616.0	51.7	172.0	187.8	15.8	0.20	0.17	0.001
	primary	656.0	730.0	74.0	199.9	222.5	22.6	0.15	0.02	0.001
ECM-340	oxide	497.0	585.5	88.5	151.5	178.5	27.0	0.31	0.26	0.003
	enriched	671.0	915.0	244.0	204.5	278.9	74.4	0.35	0.34	0.01
	enriched	1088.8	1164.5	75.7	331.9	354.9	23.1	0.12	0.09	0.012
	primary	1164.5	1894.7	730.2	354.9	577.5	222.6	0.23	0.02	0.013
	including	1781.1	1829.9	48.8	542.9	557.8	14.9	0.37	0.03	0.025
ECM-341	oxide	218.0	269.0	51.0	66.4	82.0	15.5	0.31	0.30	0.001
	enriched	271.6	312.0	40.4	82.8	95.1	12.3	1.38	1.37	0.001
	enriched	352.0	380.0	28.0	107.3	115.8	8.5	0.66	0.57	0.001
	enriched	420.0	464.8	44.8	128.0	141.7	13.7	0.46	0.44	0.001
	enriched	508.0	580.0	72.0	154.8	176.8	21.9	0.16	0.15	0.001
ECM-343	oxide	136.0	156.0	20.0	41.5	47.5	6.1	0.60	0.55	0.002
	oxide	204.2	341.7	137.5	62.2	104.2	41.9	0.32	0.26	0.001
	enriched	471.0	554.6	83.6	143.6	169.0	25.5	1.02	0.95	0.001
	enriched	621.0	745.0	124.0	189.3	227.1	37.8	0.57	0.56	0.001
	enriched	526.3	550.5	24.2	160.4	167.8	7.4	0.32	0.31	0.001
	enriched	581.0	700.0	119.0	177.1	213.4	36.3	0.16	0.15	0.001
	enriched	758.0	818.9	60.9	231.0	249.6	18.6	0.18	0.17	0.002

ECM-344	enriched	888.0	1118.0	103.0	270.7	340.8	31.4	0.13	0.11	0.004
	oxide	898.0	919.4	21.4	273.7	280.2	6.5	0.29	0.18	0.001
	primary	1148.0	1168.0	20.0	349.9	356.0	6.1	0.13	0.05	0.001
	primary	1198.0	1241.0	43.0	365.2	378.3	13.1	0.12	0.02	0.002
	primary	1268.0	1390.5	122.5	386.5	423.8	37.3	0.17	0.02	0.002
ECM-345	oxide	467.0	491.7	24.7	142.3	149.9	7.5	0.12	0.09	0.001
	enriched	568.1	588.9	20.8	173.2	179.5	6.3	0.31	0.31	0.002
	enriched	636.7	657.0	20.3	194.1	200.3	6.2	0.73	0.72	0.002
	enriched	697.9	865.9	168.0	212.7	263.9	51.2	0.35	0.33	0.002
	enriched	894.0	961.8	67.8	272.5	293.2	20.7	0.46	0.45	0.002
	enriched	1036.0	1075.0	39.0	315.8	327.7	11.9	0.61	0.58	0.005
	primary	1075.0	1107.0	32.0	327.7	337.4	9.8	0.55	0.40	0.008
	primary	1153.1	1213.0	59.9	351.5	369.7	18.3	0.10	0.03	0.001
ECM-346	oxide	150.4	204.0	53.6	45.8	62.2	16.3	0.40	0.34	0.002
	including	297.0	323.0	26.0	90.5	98.5	7.9	0.64	0.64	0.003
	enriched	297.0	363.0	66.0	90.5	110.6	20.1	0.35	0.34	0.003
	enriched	423.0	517.4	94.4	128.9	157.7	28.8	0.40	0.38	0.001
	enriched	546.7	568.0	21.3	166.6	173.1	6.5	0.68	0.67	0.001
	enriched	657.0	717.0	60.0	200.3	218.5	18.3	0.17	0.11	0.001
	enriched	758.0	788.0	30.0	231.0	240.2	9.1	0.14	0.07	0.001
ECM-347	enriched	768.0	1113.0	345.0	234.1	339.2	105.2	0.18	0.15	0.003
	primary	1180.0	1241.2	61.2	359.7	378.3	18.7	0.10	0.03	0.001
ECM-348	enriched	385.5	518.5	133.0	117.5	158.0	40.5	0.28	0.15	0.001
	including	402.1	422.5	20.4	122.6	128.8	6.2	0.67	0.37	0.001
	enriched	641.5	797.2	155.7	195.5	243.0	47.5	0.56	0.52	0.001
	primary	797.2	940.0	142.8	243.0	286.5	43.5	0.21	0.03	0.001
	including	885.7	931.0	45.3	270.0	283.8	13.8	0.38	0.04	0.002
ECM-349	enriched	512.7	533.0	20.3	156.3	162.5	6.2	0.11	0.10	0.001
	enriched	649.0	671.7	22.7	197.8	204.7	6.9	0.16	0.15	0.001
	including	698.3	755.0	56.7	212.8	230.1	17.3	0.32	0.32	0.001
	enriched	698.3	926.0	227.7	212.8	282.2	69.4	0.19	0.18	0.001
	primary	926.0	976.6	50.6	282.2	297.7	15.4	0.21	0.05	0.001
ECM-350	enriched	559.0	666.8	107.8	170.4	203.2	32.9	0.38	0.35	0.001
	enriched	756.6	850.4	93.8	230.6	259.2	28.6	0.17	0.15	0.001
	primary	850.4	901.0	50.6	259.2	274.6	15.4	0.15	0.04	0.001
	primary	931.0	999.5	68.5	283.8	304.6	20.9	0.12	0.03	0.001
ECM-351	enriched	648.0	668.0	20.0	197.5	203.6	6.1	0.24	0.23	0.001
	enriched	777.7	877.8	100.1	237.0	267.6	30.5	0.11	0.11	0.001
	enriched	986.3	1034.9	48.6	300.6	315.4	14.8	0.21	0.20	0.002
	enriched	1098.6	1270.0	171.4	334.9	387.1	52.2	0.12	0.07	0.001
	primary	1300.0	1320.0	20.0	396.2	402.3	6.1	0.11	0.02	0.001
ECM-352	enriched	458.0	619.8	161.8	139.6	188.9	49.3	1.05	0.90	0.005
	enriched	645.8	761.0	115.2	196.8	232.0	35.1	0.23	0.22	0.002
	enriched	811.0	869.0	58.0	247.2	264.9	17.7	0.10	0.10	0.005

	enriched	945.0	975.0	30.0	288.0	297.2	9.1	0.11	0.10	0.002
ECM-353	enriched	542.1	583.4	41.3	165.2	177.8	12.6	0.64	0.59	0.001
	enriched	614.5	747.0	132.5	187.3	227.7	40.4	0.21	0.15	0.001
	primary	747.0	820.0	73.0	227.7	249.9	22.3	0.20	0.05	0.001
ECM-354	unbound	418.0	454.0	36.0	127.4	138.4	11.0	0.21	0.12	0.001
	including	543.0	563.6	20.6	165.5	171.8	6.3	0.39	0.39	0.003
	enriched	543.0	598.3	55.3	165.5	182.4	16.9	0.19	0.19	0.002
	enriched	840.0	912.2	72.2	256.0	278.0	22.0	0.11	0.07	0.001
	primary	962.0	992.0	30.0	293.2	302.4	9.1	0.11	0.04	0.001
ECM-356	unbound	127.0	153.4	26.4	38.7	46.8	8.0	0.87	0.77	0.001
	enriched	405.1	460.3	55.2	123.5	140.3	16.8	0.48	0.39	0.001
	enriched	526.1	547.0	20.9	160.4	166.7	6.4	0.52	0.52	0.002
	enriched	618.0	646.5	28.5	188.4	197.1	8.7	0.29	0.29	0.001
	including	714.0	753.0	39.0	217.6	229.5	11.9	0.89	0.86	0.002
	enriched	714.0	827.5	113.5	217.6	252.2	34.6	0.38	0.35	0.001
	primary	847.5	870.0	22.5	258.3	265.2	6.9	0.11	0.02	0.001
ECM-357	enriched	365.0	428.7	63.7	111.3	130.7	19.4	0.31	0.30	0.004
	enriched	476.3	545.5	69.2	145.2	166.3	21.1	0.45	0.44	0.001
	enriched	972.5	1093.3	120.8	296.4	333.2	36.8	0.13	0.13	0.002
ECM-358	enriched	658.8	714.6	55.8	200.8	217.8	17.0	0.12	0.12	0.003
ECM-359	unbound	292.0	314.7	22.7	89.0	95.9	6.9	0.33	0.25	0.001
	enriched	378.2	474.6	96.4	115.3	144.7	29.4	0.18	0.18	0.001
	enriched	504.0	613.0	109.0	153.6	186.8	33.2	0.14	0.13	0.001
	enriched	643.0	779.0	136.0	196.0	237.4	41.5	0.14	0.10	0.001
	primary	809.0	1060.2	251.2	246.6	323.1	76.6	0.21	0.05	0.001
	including	882.0	902.0	20.0	268.8	274.9	6.1	0.35	0.05	0.001
	and	912.0	932.0	20.0	278.0	284.1	6.1	0.37	0.06	0.002
ECM-360	leached	147.0	167.0	20.0	44.8	50.9	6.1	0.13	0.06	0.001
	oxide	348.0	387.0	39.0	106.1	118.0	11.9	0.30	0.21	0.001
	oxide	417.0	555.0	138.0	127.1	169.2	42.1	0.33	0.27	0.004
	including	447.0	469.0	22.0	136.2	143.0	6.7	0.66	0.55	0.008
ECM-361	enriched	264.5	331.8	67.3	80.6	101.1	20.5	0.21	0.19	0.004
	enriched	407.3	492.0	84.7	124.1	150.0	25.8	0.21	0.20	0.002
	including	538.0	561.3	23.3	164.0	171.1	7.1	0.57	0.56	0.001
	enriched	538.0	700.5	162.5	164.0	213.5	49.5	0.20	0.19	0.001
	enriched	730.0	797.7	67.7	222.5	243.1	20.6	0.25	0.24	0.001
	including	770.5	797.7	27.2	234.8	243.1	8.3	0.50	0.48	0.001
	enriched	855.2	880.7	25.5	260.7	268.4	7.8	0.28	0.27	0.001
	enriched	948.7	1032.1	83.4	289.2	314.6	25.4	0.36	0.34	0.002
ECM-362	oxide	699.0	809.0	110.0	213.1	246.6	33.5	0.34	0.32	0.008
	including	779.0	799.0	20.0	237.4	243.5	6.1	0.89	0.89	0.01
	enriched	946.0	985.0	39.0	288.3	300.2	11.9	1.18	1.14	0.012
	enriched	1103.6	1317.5	213.9	336.4	401.6	65.2	0.45	0.40	0.015
	primary	1317.5	1350.0	32.5	401.6	411.5	9.9	0.23	0.05	0.026

ECM-363	oxide	570.4	633.7	63.3	173.9	193.2	19.3	0.73	0.72	0.008
	including	763.0	785.6	22.6	232.6	239.5	6.9	0.77	0.74	0.01
	enriched	763.0	1025.2	262.2	232.6	312.5	79.9	0.30	0.29	0.005
	and	833.4	858.0	24.6	254.0	261.5	7.5	0.61	0.59	0.004
	enriched	1055.8	1190.0	134.2	321.8	362.7	40.9	0.88	0.61	0.017
	primary	1190.0	1220.0	30.0	362.7	371.9	9.1	0.30	0.05	0.029
ECM-364	unbound	674.7	702.0	27.3	205.6	214.0	8.3	0.48	0.36	0.002
	oxide	702.0	805.7	103.7	214.0	245.6	31.6	0.99	0.86	0.018
	including	783.7	805.7	22.0	238.9	245.6	6.7	2.67	2.30	0.013
	enriched	888.7	960.4	71.7	270.9	292.7	21.9	0.90	0.89	0.006
	enriched	1000.0	1331.0	331.0	304.8	405.7	100.9	1.01	0.76	0.032
	primary	1331.0	1410.0	79.0	405.7	429.8	24.1	0.47	0.06	0.098
ECM-366	enriched	579.2	647.0	67.8	176.5	197.2	20.7	1.90	2.08	0.001
	enriched	717.0	762.0	45.0	218.5	232.3	13.7	0.32	0.12	0.001
	primary	762.0	790.0	28.0	232.3	240.8	8.5	0.15	0.05	0.001
ECM-367	oxide	526.4	575.0	48.6	160.4	175.3	14.8	0.42	0.41	0.007
	including	615.7	656.0	40.3	187.7	199.9	12.3	0.97	0.96	0.003
	enriched	615.7	1305.3	689.6	187.7	397.9	210.2	0.62	0.41	0.026
	and	1021.0	1041.0	20.0	311.2	317.3	6.1	1.37	1.35	0.007
	and	1219.7	1305.3	85.6	371.8	397.9	26.1	1.05	0.08	0.111
	primary	1315.0	1390.0	75.0	400.8	423.7	22.9	1.23	0.08	0.134
ECM-368	enriched	771.0	818.0	47.0	235.0	249.3	14.3	0.61	0.59	0.007
	enriched	988.0	1037.0	49.0	301.1	316.1	14.9	0.53	0.50	0.016
	enriched	1067.0	1136.0	69.0	325.2	346.3	21.0	0.67	0.65	0.017
	enriched	1215.0	1255.0	40.0	370.3	382.5	12.2	0.29	0.28	0.011
	enriched	1432.0	1593.0	161.0	436.5	485.5	49.1	1.50	1.41	0.04
	including	1443.9	1504.0	60.1	440.1	458.4	18.3	2.92	2.89	0.063
	primary	1593.0	1660.2	67.2	485.5	506.0	20.5	0.48	0.05	0.058
ECM-369	enriched	474.0	586.0	112.0	144.5	178.6	34.1	0.35	0.31	0.001
	including	480.2	503.0	22.8	146.4	153.3	6.9	0.85	0.83	0.001
	primary	633.0	663.0	30.0	192.9	202.1	9.1	0.11	0.02	0.001
	primary	693.0	886.0	193.0	211.2	270.1	58.8	0.12	0.02	0.001
	including	852.0	876.0	24.0	259.7	267.0	7.3	0.20	0.02	0.001
	primary	916.0	960.0	44.0	279.2	292.6	13.4	0.32	0.02	0.001
ECM-371	unbound	334.0	354.0	20.0	101.8	107.9	6.1	0.11	0.04	0.001
	enriched	731.3	771.0	39.7	222.9	235.0	12.1	0.79	0.77	0.017
	enriched	800.0	1105.0	305.0	243.8	336.8	93.0	0.74	0.72	0.029
	including	840.1	880.0	39.9	256.1	268.2	12.2	2.13	2.11	0.111
	primary	1105.0	1282.2	177.2	336.8	390.8	54.0	0.21	0.03	0.004
	including	1198.0	1218.0	20.0	365.2	371.2	6.1	0.50	0.04	0.01
ECM-372	enriched	507.5	718.0	210.5	154.7	218.8	64.2	0.34	0.31	0.001
	enriched	777.0	897.0	120.0	236.8	273.4	36.6	0.11	0.09	0.001
ECM-373	oxide	714.2	742.2	28.0	217.7	226.2	8.5	0.49	0.47	0.002
	enriched	1212.7	1448.0	235.3	369.6	441.4	71.7	1.06	1.01	0.03

ECM-373	including	1316.8	1378.0	61.2	401.4	420.0	18.7	1.81	1.78	0.039
	primary	1448.0	1620.0	172.0	441.4	493.8	52.4	0.53	0.04	0.011
ECM-374	unbound	267.0	287.0	20.0	81.4	87.5	6.1	0.19	0.12	0.001
	enriched	644.1	736.0	91.9	196.3	224.3	28.0	0.76	0.74	0.002
	including	761.1	784.5	23.4	232.0	239.1	7.1	1.52	1.50	0.002
	enriched	761.1	1006.0	244.9	232.0	306.6	74.6	0.39	0.38	0.002
ECM-375	oxide	398.0	427.0	29.0	121.3	130.1	8.8	0.23	0.22	0.001
	enriched	522.0	857.0	335.0	159.1	261.2	102.1	0.34	0.33	0.003
	including	590.3	624.0	33.7	179.9	190.2	10.3	0.83	0.82	0.003
ECM-376	oxide	604.0	647.5	43.5	184.1	197.4	13.3	0.51	0.46	0.002
	including	647.5	695.0	47.5	197.4	211.8	14.5	0.33	0.31	0.001
	enriched	647.5	883.0	235.5	197.4	269.1	71.8	0.22	0.21	0.001
	enriched	916.0	982.2	66.2	279.2	299.4	20.2	0.18	0.18	0.001
	primary	1209.0	1239.0	30.0	368.5	377.6	9.1	0.23	0.05	0.001
ECM-377	oxide	554.0	704.0	150.0	168.9	214.6	45.7	0.39	0.35	0.014
	enriched	737.3	1033.0	295.7	224.7	314.9	90.1	0.46	0.44	0.007
	including	954.1	1023.6	69.5	290.8	312.0	21.2	0.88	0.87	0.008
	enriched	1138.0	1158.0	20.0	346.9	353.0	6.1	0.26	0.25	0.021
	enriched	1198.0	1438.2	240.2	365.2	438.4	73.2	1.02	0.73	0.047
	including	1201.5	1258.0	56.5	366.2	383.4	17.2	1.76	1.71	0.028
ECM-378	enriched	488.0	526.8	38.8	148.7	160.6	11.8	0.30	0.28	0.014
	including	558.0	638.0	80.0	170.1	194.5	24.4	1.08	1.03	0.004
	enriched	558.0	888.6	330.6	170.1	270.8	100.8	0.69	0.67	0.004
	including	913.8	948.3	34.5	278.5	289.0	10.5	0.88	0.85	0.004
	enriched	913.8	1138.0	224.2	278.5	346.9	68.3	0.37	0.30	0.006
	enriched	1188.0	1350.0	162.0	362.1	411.5	49.4	0.19	0.11	0.004
ECM-380	leached	317.2	348.5	31.3	96.7	106.2	9.5	0.17	0.08	0.001
	enriched	549.8	861.4	311.6	167.6	262.6	95.0	0.39	0.38	0.001
	primary	1010.0	1202.0	192.0	307.8	366.4	58.5	0.12	0.01	0.001
ECM-381	oxide	488.0	508.0	20.0	148.7	154.8	6.1	0.14	0.13	0.004
	enriched	695.0	758.0	63.0	211.8	231.0	19.2	0.60	0.57	0.007
	enriched	788.0	958.0	170.0	240.2	292.0	51.8	0.55	0.54	0.003
	including	858.0	878.0	20.0	261.5	267.6	6.1	0.99	0.99	0.003
	enriched	988.0	1327.0	339.0	301.1	404.5	103.3	0.88	0.64	0.012
	including	1128.0	1158.0	30.0	343.8	353.0	9.1	1.84	1.69	0.006
	and	1208.0	1236.8	28.8	368.2	377.0	8.8	1.44	1.18	0.012
	primary	1327.0	1410.0	83.0	404.5	429.8	25.3	0.68	0.05	0.044
ECM-382	enriched	690.0	1273.0	583.0	210.3	388.0	177.7	0.62	0.56	0.008
	including	732.0	763.9	31.9	223.1	232.8	9.7	1.01	0.99	0.004
	and	813.0	865.0	52.0	247.8	263.7	15.8	1.30	1.29	0.003
	enriched	1303.0	1330.0	27.0	397.2	405.4	8.2	0.42	0.17	0.002
ECM-383	unbound	360.7	389.9	29.2	109.9	118.8	8.9	0.18	0.06	0.001
	enriched	759.8	896.0	136.2	231.6	273.1	41.5	0.11	0.10	0.002
	enriched	921.8	959.0	37.2	281.0	292.3	11.3	0.13	0.05	0.002

ECM-384	enriched	722.0	755.2	33.2	220.1	230.2	10.1	0.15	0.15	0.002
	including	788.4	928.0	139.6	240.3	282.9	42.6	1.16	1.14	0.024
	enriched	788.4	1160.9	372.5	240.3	353.8	113.5	0.63	0.57	0.012
ECM-385	oxide	985.0	1025.0	40.0	300.2	312.4	12.2	0.68	0.54	0.002
	oxide	1155.7	1248.5	92.8	352.3	380.5	28.3	0.70	0.68	0.028
	including	1220.0	1240.0	20.0	371.9	378.0	6.1	1.94	1.87	0.029
	enriched	1248.5	1381.9	133.4	380.5	421.2	40.7	0.85	0.48	0.076
	primary	1381.9	1420.0	38.1	421.2	432.8	11.6	0.77	0.06	0.026
ECM-386	including	379.9	400.0	20.1	115.8	121.9	6.1	0.47	0.42	0.003
	oxide	379.9	507.0	127.1	115.8	154.5	38.7	0.23	0.20	0.001
ECM-387	enriched	295.2	342.0	46.8	90.0	104.2	14.3	0.31	0.30	0.005
	oxide	358.5	517.0	158.5	109.3	157.6	48.3	0.32	0.27	0.001
	including	457.0	487.0	30.0	139.3	148.4	9.1	0.57	0.57	0.001
ECM-388	enriched	254.0	291.0	37.0	77.4	88.7	11.3	0.12	0.12	0.002
	including	341.4	389.4	48.0	104.1	118.7	14.6	0.52	0.28	0.001
	oxide	341.4	572.2	230.8	104.1	174.4	70.3	0.26	0.19	0.003
ECM-389	oxide	250.2	287.0	36.8	76.3	87.5	11.2	0.34	0.23	0.003
ECM-390	enriched	917.1	955.7	38.6	279.5	291.3	11.8	0.66	0.61	0.003
ECM-391	oxide	348.1	389.0	40.9	106.1	118.6	12.5	0.17	0.11	0.002
ECM-392	oxide	301.9	323.0	21.1	92.0	98.5	6.4	0.31	0.21	0.001
ECM-393	oxide	219.0	281.0	62.0	66.8	85.6	18.9	0.13	0.06	0.001
	oxide	351.0	515.0	164.0	107.0	157.0	50.0	0.38	0.31	0.009
	including	415.0	435.0	20.0	126.5	132.6	6.1	0.93	0.86	0.012
ECM-394	oxide	193.0	368.0	175.0	58.8	112.2	53.3	0.33	0.25	0.003
	including	280.0	310.0	30.0	85.3	94.5	9.1	0.62	0.54	0.003
	oxide	418.0	500.2	82.2	127.4	152.5	25.1	0.51	0.40	0.007
ECM-395	oxide	227.0	276.0	49.0	69.2	84.1	14.9	0.26	0.12	0
ECM-396	oxide	316.0	382.7	44.3	96.3	116.6	13.5	0.32	0.27	0.002
	oxide	413.8	450.5	36.7	126.1	137.3	11.2	0.61	0.55	0.005
ECM-397	oxide	428.2	548.0	119.8	130.5	167.0	36.5	0.37	0.31	0.003
	including	485.0	525.0	40.0	147.8	160.0	12.2	0.75	0.71	0.003
ECM-398	enriched	732.3	803.0	70.7	223.2	244.8	21.5	0.61	0.60	0.001
	including	756.0	776.0	20.0	230.4	236.5	6.1	1.44	1.41	0.001
ECM-399	enriched	376.0	540.0	164.0	114.6	164.6	50.0	0.55	0.53	0.001
ECM-400	oxide	322.0	352.0	30.0	98.1	107.3	9.1	0.24	0.18	0.001
	oxide	542.0	660.0	85.0	165.2	201.2	25.9	0.31	0.24	0.001
ECM-401	oxide	567.0	591.0	24.0	172.8	180.1	7.3	0.80	0.75	0.001
	including	591.0	613.2	22.2	180.1	186.9	6.8	2.45	2.42	0.006
	enriched	591.0	663.0	72.0	180.1	202.1	21.9	1.02	1.01	0.003
	primary	673.0	702.7	29.7	205.1	214.2	9.1	0.20	0.05	0.001
ECM-402	oxide	245.0	285.0	40.0	74.7	86.9	12.2	0.19	0.12	0.001
	oxide	363.8	462.0	51.4	110.9	140.8	15.7	0.22	0.16	0.001
ECM-403	oxide	635.2	775.3	140.1	193.6	236.3	42.7	0.30	0.23	0.003
	including	665.0	685.0	20.0	202.7	208.8	6.1	0.49	0.36	0.002

ECM-404	oxide	257.0	362.0	105.0	78.3	110.3	32.0	0.235	0.155	0.001
	enriched	487.3	603.5	116.2	148.5	183.9	35.4	0.437	0.366	0.001
ECM-405	oxide	213.8	242.6	28.8	65.2	73.9	8.8	0.19	0.186	0.002
	oxide	268.4	378.0	109.6	81.8	115.2	33.4	0.139	0.088	0.001
	including	449.1	476.4	27.3	136.9	145.2	8.3	0.685	0.643	0.001
	enriched	449.1	526.0	76.9	136.9	160.3	23.4	0.328	0.251	0.001
	primary	566.0	594.3	28.3	172.5	181.1	8.6	0.141	0.031	0.001
ECM-406	oxide	226.0	301.0	75.0	68.9	91.7	22.9	0.19	0.11	0.001
	enriched	409.6	565.6	156.0	124.8	172.4	47.5	0.23	0.18	0.001
	oxide	565.6	680.0	114.4	172.4	207.3	34.9	0.35	0.32	0.006
ECM-407	unbound	377.0	421.1	44.1	114.9	128.4	13.4	0.13	0.06	0.001
	oxide	421.1	449.4	28.3	128.4	137.0	8.6	0.22	0.20	0.001
ECM-408	enriched	264.2	313.3	49.1	80.5	95.5	15.0	0.39	0.373	0.002
	enriched	483.0	503.0	20.0	147.2	153.3	6.1	0.119	0.028	0.005
	oxide	503.0	550.5	47.5	153.3	167.8	14.5	0.593	0.531	0.006
ECM-409	including	423.5	450.7	27.2	129.1	137.4	8.3	1.03	1.02	0.001
	enriched	423.5	525.0	101.5	129.1	160.0	30.9	0.35	0.31	0.001
	primary	566.5	600.0	33.5	172.7	182.9	10.2	0.26	0.03	0.001
ECM-410	oxide	318.0	682.0	190.6	96.9	207.9	58.1	0.51	0.45	0.003
ECM-411	oxide	229.4	714.0	135.6	69.9	217.6	41.3	0.40	0.36	0.004
	enriched	500.0	645.0	145.0	152.4	196.6	44.2	0.69	0.62	0.005
ECM-412	oxide	197.0	580.4	127.6	60.0	176.9	38.9	0.295	0.201	0.003
	enriched	251.1	280.3	29.2	76.5	85.4	8.9	0.355	0.344	0.002
	enriched	439.9	506.9	67.0	134.1	154.5	20.4	0.446	0.403	0.001
ECP-301	leached	1226.8	1256.8	30.0	373.9	383.1	9.1	0.14	0.05	0.006
	oxide	1256.8	1623.0	366.2	383.1	494.7	111.6	0.61	0.56	0.003
	including	1336.4	1416.2	79.8	407.3	431.7	24.3	1.75	1.73	0.004
	including	1649.9	1687.0	37.1	502.9	514.2	11.3	0.27	0.26	0.004
	oxide	1649.9	1753.8	103.9	502.9	534.6	31.7	0.16	0.15	0.002
	enriched	1758.2	1787.0	28.8	535.9	544.7	8.8	0.19	0.09	0.001
	unbound	2352.0	2382.0	30.0	716.9	726.0	9.1	0.12	0.02	0.001
ECP-312	unbound	1532.0	2327.8	47.3	467.0	709.5	14.4	0.45	0.37	0.001
	enriched	1813.0	2065.0	252.0	552.6	629.4	76.8	0.36	0.21	0.003
	primary	2065.0	2266.0	201.0	629.4	690.7	61.3	0.21	0.02	0.006
	including	2075.0	2105.0	30.0	632.5	641.6	9.1	0.41	0.03	0.001
ECP-314	enriched	1396.2	1604.0	207.8	425.6	488.9	63.3	0.45	0.44	0.002
	including	1416.0	1436.0	20.0	431.6	437.7	6.1	1.34	1.32	0.004
ECP-315	enriched	1146.0	1296.0	150.0	349.3	395.0	45.7	0.30	0.29	0.001
	enriched	1376.0	1560.5	184.5	419.4	475.6	56.2	0.20	0.20	0.001
ECP-316	enriched	2003.0	2038.0	35.0	610.5	621.2	10.7	0.20	0.17	0.01
	primary	2038.0	2396.6	358.6	621.2	730.5	109.3	0.23	0.03	0.009
	including	2123.8	2230.0	106.2	647.3	679.7	32.4	0.39	0.04	0.005
ECP-317	enriched	1278.0	1469.4	191.4	389.5	447.9	58.3	0.37	0.37	0.002
	including	1308.0	1328.0	20.0	398.7	404.8	6.1	0.75	0.74	0.001

ECP-319	oxide	1350.5	1581.0	230.5	411.6	481.9	70.3	0.92	0.90	0.011
	including	1402.7	1475.0	72.3	427.5	449.6	22.0	1.83	1.80	0.014
	enriched	1612.0	1652.0	40.0	491.3	503.5	12.2	0.13	0.09	0.001
ECP-321	unbound	1148.0	1176.7	28.7	349.9	358.7	8.7	0.26	0.19	0.008
	enriched	1200.0	1225.5	25.5	365.8	373.5	7.8	1.73	1.70	0.011
	including	1405.6	1435.0	29.4	428.4	437.4	9.0	2.50	2.48	0.022
	enriched	1405.6	1640.0	234.4	428.4	499.9	71.4	0.57	0.49	0.01
	including	1640.0	1674.3	34.3	499.9	510.3	10.5	0.56	0.07	0.016
	primary	1640.0	1824.0	184.0	499.9	556.0	56.1	0.23	0.03	0.008
	primary	1864.0	1995.4	131.4	568.1	608.2	40.1	0.47	0.06	0.008
ECP-324	primary	2078.0	2148.0	70.0	633.4	654.7	21.3	0.12	0.01	0.005
	enriched	1764.0	1810.0	46.0	537.7	551.7	14.0	0.19	0.18	0.001
ECP-327	including	758.7	895.0	136.3	231.3	272.8	41.5	0.86	0.84	0.012
	enriched	758.7	1291.0	532.3	231.3	393.5	162.2	0.37	0.34	0.005
	primary	1676.0	1726.0	50.0	510.8	526.1	15.2	0.15	0.01	0.004
ECP-329	enriched	795.0	1475.0	680.0	242.3	449.6	207.3	0.62	0.49	0.005
	including	811.8	983.0	171.2	247.4	299.6	52.2	1.40	1.16	0.012
	and	1055.0	1075.0	20.0	321.6	327.7	6.1	1.10	1.09	0.006
	primary	1475.0	1555.0	80.0	449.6	474.0	24.4	0.15	0.04	0.002
	primary	1655.0	1705.0	50.0	504.4	519.7	15.2	0.15	0.03	0.002
ECP-365	oxide	1224.0	1405.0	181.0	373.1	428.2	55.2	0.75	0.73	0.006
	including	1236.0	1306.7	70.7	376.7	398.3	21.5	1.41	1.38	0.007
	oxide	1445.0	1465.0	20.0	440.4	446.5	6.1	0.86	0.86	0.004
	oxide	1547.0	1645.8	98.8	471.5	501.6	30.1	0.44	0.40	0.002
	enriched	1645.8	1674.8	29.0	501.6	510.5	8.8	0.46	0.44	0.004
	primary	1674.8	1697.5	22.7	510.5	517.4	6.9	0.16	0.02	0.002

Cactus West

Holeid	Zone	From	To	Length	From	To	Length	CuT	CuTsol	Mo
		Feet			Meters			Grade (%)		
ECW-270	enriched	537.0	605.7	68.7	163.7	184.6	20.9	0.32	0.31	0.001
ECW-271	primary	1528.0	1682.0	154.0	465.7	512.7	46.9	0.21	0.04	0.011
	including	1618.0	1651.0	33.0	493.2	503.2	10.1	0.42	0.03	0.010
ECW-272	oxide	748.2	770.0	21.8	228.1	234.7	6.6	0.12	0.07	0.002
	oxide	872.0	983.2	111.2	265.8	299.7	33.9	0.11	0.08	0.002
	oxide	1223.0	1286.3	63.3	372.8	392.1	19.3	0.11	0.11	0.006
	enriched	1286.3	1336.0	49.7	392.1	407.2	15.1	0.26	0.09	0.012
	primary	1336.0	1645.9	309.9	407.2	501.7	94.5	0.15	0.02	0.005
ECW-273	oxide	1334.0	1357.0	23.0	406.6	413.6	7.0	0.20	0.19	0.014
	enriched	1357.0	1459.0	102.0	413.6	444.7	31.1	0.34	0.24	0.012
	primary	1459.0	1552.0	93.0	444.7	473.0	28.3	0.32	0.05	0.032
	including	1459.0	1498.6	39.6	444.7	456.8	12.1	0.62	0.10	0.027
	oxide	822.0	933.0	111.0	250.5	284.4	33.8	0.23	0.10	0.001
	including	849.0	889.0	40.0	258.8	271.0	12.2	0.33	0.14	0.001

ECW-274	oxide	983.0	1121.4	138.4	299.6	341.8	42.2	0.15	0.10	0.001
	enriched	1121.4	1217.0	95.6	341.8	370.9	29.1	0.12	0.09	0.001
	primary	1402.6	1605.0	202.4	427.5	489.2	61.7	0.34	0.03	0.010
	including	1505.0	1605.0	100.0	458.7	489.2	30.5	0.49	0.04	0.012
ECW-275	oxide	690.0	730.4	40.4	210.3	222.6	12.3	0.74	0.71	0.001
	primary	750.0	814.0	64.0	228.6	248.1	19.5	0.12	0.05	0.001
	primary	990.0	1270.6	280.6	301.8	387.3	85.5	0.19	0.02	0.001
	including	1216.0	1270.6	54.6	370.6	387.3	16.6	0.36	0.03	0.003
ECW-276	oxide	654.0	800.0	146.0	199.3	243.8	44.5	0.13	0.09	0.002
	enriched	826.4	1023.0	196.6	251.9	311.8	59.9	0.43	0.14	0.008
	primary	1023.0	1648.2	625.2	311.8	502.4	190.6	0.39	0.05	0.014
	including	1174.5	1207.1	32.6	358.0	367.9	9.9	0.62	0.06	0.012
	and	1285.0	1364.2	79.2	391.7	415.8	24.1	0.67	0.06	0.012
ECW-277	oxide	1018.0	1149.3	131.3	310.3	350.3	40.0	0.17	0.11	0.003
	enriched	1149.3	1254.8	105.5	350.3	382.5	32.2	0.20	0.10	0.004
	primary	1254.8	1665.0	410.2	382.5	507.5	125.0	0.18	0.02	0.007
	including	1254.8	1295.0	40.2	382.5	394.7	12.3	0.51	0.05	0.004
ECW-278	enriched	222.4	325.5	103.1	67.8	99.2	31.4	0.20	0.19	0.001
	primary	325.5	1115.8	790.3	99.2	340.1	240.9	0.19	0.03	0.002
	including	477.0	515.0	38.0	145.4	157.0	11.6	0.63	0.07	0.001
	and	1054.0	1115.8	61.8	321.3	340.1	18.8	0.43	0.06	0.013
ECW-279	enriched	975.0	1016.0	41.0	297.2	309.7	12.5	0.25	0.24	0.001
	enriched	1127.0	1165.0	38.0	343.5	355.1	11.6	0.38	0.34	0.001
	primary	1357.0	1405.2	48.2	413.6	428.3	14.7	0.19	0.02	0.004
ECW-280	enriched	280.0	314.0	34.0	85.3	95.7	10.4	0.37	0.33	0.001
	oxide	314.0	370.0	56.0	95.7	112.8	17.1	0.11	0.07	0.001
	primary	370.0	409.5	39.5	112.8	124.8	12.0	0.14	0.06	0.001
	primary	463.0	528.0	65.0	141.1	160.9	19.8	0.25	0.02	0.001
	primary	573.3	718.0	144.7	174.7	218.8	44.1	0.13	0.01	0.001
	primary	788.0	1069.9	281.9	240.2	326.1	85.9	0.16	0.02	0.001
ECW-281	enriched	983.3	1093.0	109.7	299.7	333.1	33.4	0.20	0.18	0.001
	primary	1434.2	1648.2	214.0	437.1	502.4	65.2	0.15	0.02	0.002
	including	1578.0	1627.0	49.0	481.0	495.9	14.9	0.26	0.03	0.004
ECW-282	oxide	906.7	986.0	79.3	276.4	300.5	24.2	0.12	0.06	0.006
	enriched	986.0	1107.0	121.0	300.5	337.4	36.9	0.20	0.17	0.004
	primary	1107.0	1615.0	508.0	337.4	492.3	154.8	0.17	0.02	0.003
	including	1193.0	1233.0	40.0	363.6	375.8	12.2	0.33	0.03	0.003
	and	1468.0	1505.0	37.0	447.4	458.7	11.3	0.45	0.04	0.004
	and	1575.0	1615.0	40.0	480.1	492.3	12.2	0.37	0.02	0.005
ECW-283	No Significant Intercepts									
ECW-284	oxide	690.0	1018.0	328.0	210.3	310.3	100.0	0.22	0.18	0.006
	including	792.0	834.9	42.9	241.4	254.5	13.1	0.45	0.41	0.005
	enriched	1018.0	1120.0	102.0	310.3	341.4	31.1	0.33	0.25	0.005
	primary	1120.0	1373.4	253.4	341.4	418.6	77.2	0.30	0.03	0.007

	including	1304.0	1354.0	50.0	397.5	412.7	15.2	0.41	0.03	0.006
ECW-286	oxide	839.4	900.5	61.1	255.8	274.5	18.6	0.48	0.42	0.004
	enriched	900.5	980.0	79.5	274.5	298.7	24.2	0.48	0.40	0.008
	primary	980.0	1348.0	368.0	298.7	410.9	112.2	0.36	0.05	0.014
	including	984.4	1034.0	49.6	300.0	315.2	15.1	0.44	0.04	0.002
	and	1135.0	1184.4	49.4	345.9	361.0	15.1	0.51	0.04	0.017
	primary	1472.0	1546.0	74.0	448.7	471.2	22.6	0.13	0.01	0.005
ECW-288	enriched	864.4	1019.7	155.3	263.5	310.8	47.3	0.33	0.19	0.008
	including	985.2	1019.7	34.5	300.3	310.8	10.5	0.61	0.13	0.030
	primary	1019.7	1268.0	248.3	310.8	386.5	75.7	0.39	0.04	0.017
	including	1019.7	1072.0	52.3	310.8	326.7	15.9	0.61	0.06	0.040
ECW-290	enriched	234.4	346.0	111.6	71.4	105.5	34.0	0.23	0.21	0.001
	including	234.4	269.0	34.6	71.4	82.0	10.5	0.44	0.42	0.001
	primary	346.0	419.0	73.0	105.5	127.7	22.3	0.14	0.02	0.001
	primary	544.0	987.0	443.0	165.8	300.8	135.0	0.12	0.02	0.001
ECW-292	enriched	1013.6	1061.6	48.0	308.9	323.6	14.6	0.17	0.17	0.001
ECW-294	enriched	355.0	707.0	352.0	108.2	215.5	107.3	0.32	0.30	0.001
	including	368.3	418.0	49.7	112.3	127.4	15.1	1.59	1.56	0.001
	primary	707.0	1054.8	347.8	215.5	321.5	106.0	0.13	0.02	0.001
ECW-297	oxide	1384.0	1447.4	63.4	421.8	441.2	19.3	0.28	0.25	0.002
	enriched	1447.4	1565.3	117.9	441.2	477.1	35.9	0.43	0.34	0.003
	oxide	1565.3	1590.4	25.1	477.1	484.8	7.7	0.35	0.31	0.003
ECW-300	enriched	982.0	1211.5	229.5	299.3	369.3	70.0	0.30	0.17	0.013
ECW-303	enriched	233.0	427.8	194.8	71.0	130.4	59.4	0.17	0.16	0.001
	including	233.0	258.0	25.0	71.0	78.6	7.6	0.74	0.74	0.001
	primary	482.2	557.0	74.8	147.0	169.8	22.8	0.18	0.02	0.001
	primary	668.0	844.0	176.0	203.6	257.3	53.6	0.20	0.03	0.001
ECE-305	oxide	1172.0	1318.1	146.1	357.2	401.8	44.5	1.55	1.49	0.015
	including	1253.0	1318.1	65.1	381.9	401.8	19.8	2.20	2.19	0.020
	enriched	1323.8	1805.0	481.2	403.5	550.2	146.7	1.00	0.95	0.024
	including	1323.8	1350.0	26.2	403.5	411.5	8.0	3.30	3.25	0.042
	and	1399.0	1447.0	48.0	426.4	441.0	14.6	2.37	2.33	0.030
	and	1503.8	1537.0	33.2	458.4	468.5	10.1	1.85	1.77	0.033
	primary	1805.0	1933.0	128.0	550.2	589.2	39.0	0.29	0.04	0.024
	including	1882.7	1933.0	50.3	573.8	589.2	15.3	0.45	0.06	0.037
ECW-309	enriched	434.0	464.0	30.0	132.3	141.4	9.1	0.12	0.11	0.002
	enriched	504.0	654.0	150.0	153.6	199.3	45.7	0.20	0.19	0.002
	primary	836.0	1108.0	272.0	254.8	337.7	82.9	0.22	0.03	0.008
	including	906.0	961.0	55.0	276.1	292.9	16.8	0.36	0.04	0.007
	and	1048.0	1098.0	50.0	319.4	334.7	15.2	0.36	0.04	0.024
ECW-313	enriched	685.4	873.0	187.6	208.9	266.1	57.2	0.33	0.24	0.013
	including	685.4	719.0	33.6	208.9	219.2	10.2	0.59	0.57	0.013
	primary	873.0	1135.6	262.6	266.1	346.1	80.0	0.39	0.04	0.011
	including	974.0	1030.0	56.0	296.9	313.9	17.1	0.84	0.07	0.017

ECW-318	oxide	583.5	617.5	34.0	177.9	188.2	10.4	0.28	0.24	0.008
	oxide	676.5	800.0	123.5	206.2	243.8	37.6	0.26	0.25	0.003
	including	690.0	730.0	40.0	210.3	222.5	12.2	0.64	0.62	0.003
	enriched	1114.0	1145.0	31.0	339.5	349.0	9.4	0.90	0.82	0.008
	primary	1145.0	1794.8	649.8	349.0	547.1	198.1	0.29	0.02	0.006
	including	1165.0	1270.0	105.0	355.1	387.1	32.0	0.51	0.04	0.006
	and	1320.0	1420.0	100.0	402.3	432.8	30.5	0.51	0.04	0.006
ECW-322	oxide	137.1	243.0	105.9	41.8	74.1	32.3	0.13	0.07	0.001
	oxide	425.0	632.0	207.0	129.5	192.6	63.1	0.11	0.08	0.002
	enriched	632.0	662.0	30.0	192.6	201.8	9.1	0.15	0.12	0.004
	primary	662.0	845.0	183.0	201.8	257.6	55.8	0.22	0.04	0.009
	enriched	845.0	1073.3	228.3	257.6	327.1	69.6	0.32	0.15	0.011
	including	917.4	958.0	40.6	279.6	292.0	12.4	0.54	0.30	0.011
	primary	1073.3	1642.3	569.0	327.1	500.6	173.4	0.27	0.04	0.011
ECW-326	enriched	545.4	607.0	61.6	166.2	185.0	18.8	0.53	0.52	0.002
	including	545.4	567.0	21.6	166.2	172.8	6.6	1.08	1.07	0.002
	enriched	630.6	740.0	109.4	192.2	225.6	33.3	0.14	0.14	0.003
	enriched	821.0	931.0	110.0	250.2	283.8	33.5	0.27	0.18	0.006
	enriched	931.0	2630.9	1699.9	283.8	801.9	518.1	0.32	0.03	0.006
	and	2373.0	2419.0	46.0	723.3	737.3	14.0	0.56	0.03	0.006
	and	2513.4	2605.0	91.6	766.1	794.0	27.9	0.45	0.03	0.009
ECW-335	enriched	547.6	855.0	307.4	166.9	260.6	93.7	0.17	0.12	0.003
	primary	855.0	2307.5	1452.5	260.6	703.3	442.7	0.27	0.03	0.003
	including	1018.5	1198.0	179.5	310.4	365.2	54.7	0.38	0.04	0.005
	and	2053.0	2090.5	37.5	625.8	637.2	11.4	0.68	0.06	0.004
	and	2223.0	2307.5	84.5	677.6	703.3	25.8	0.57	0.04	0.006
ECW-342	enriched	239.8	368.2	128.4	73.1	112.2	39.1	0.41	0.40	0.001
	including	328.0	361.6	33.6	100.0	110.2	10.2	0.69	0.69	0.002
	enriched	402.0	547.5	145.5	122.5	166.9	44.3	0.31	0.26	0.004
	including	402.0	446.0	44.0	122.5	135.9	13.4	0.62	0.59	0.004
	primary	547.5	1921.6	1374.1	166.9	585.7	418.8	0.29	0.02	0.004
	including	758.0	838.0	80.0	231.0	255.4	24.4	0.46	0.03	0.004
	and	1017.0	1107.0	90.0	310.0	337.4	27.4	0.51	0.03	0.009
ECW-342	primary	1808.0	2118.0	310.0	551.1	645.6	94.5	0.44	0.03	0.004
	including	2038.0	2088.0	50.0	621.2	636.4	15.2	0.87	0.05	0.004
ECW-355	oxide	482.4	577.8	95.4	147.0	176.1	29.1	0.29	0.24	0.008
	including	497.8	527.8	30.0	151.7	160.9	9.1	0.61	0.56	0.005
	enriched	582.4	632.8	50.4	177.5	192.9	15.4	0.74	0.71	0.010
	oxide	679.2	740.0	60.8	207.0	225.6	18.5	0.22	0.18	0.004
	enriched	770.0	875.0	105.0	234.7	266.7	32.0	0.36	0.14	0.009
	including	815.0	855.0	40.0	248.4	260.6	12.2	0.49	0.11	0.007
	primary	875.0	2427.8	1552.8	266.7	740.0	473.3	0.41	0.03	0.010
	including	901.0	931.0	30.0	274.6	283.8	9.1	0.62	0.07	0.004
	and	1498.0	1558.0	60.0	456.6	474.9	18.3	0.61	0.05	0.009

	and	1738.0	2012.0	274.0	529.7	613.3	83.5	0.61	0.04	0.007
ECW-370	oxide	454.8	481.4	26.6	138.6	146.7	8.1	0.41	0.37	0.002
	enriched	531.8	581.0	49.2	162.1	177.1	15.0	0.44	0.43	0.013
	enriched	706.3	778.7	72.4	215.3	237.3	22.1	0.30	0.15	0.007
	primary	778.7	2097.8	1319.1	237.3	639.4	402.1	0.40	0.04	0.012
	including	1454.0	1499.7	45.7	443.2	457.1	13.9	0.72	0.05	0.004
ECW-379	oxide	695.0	756.5	61.5	211.8	230.6	18.7	0.24	0.17	0.005
	oxide	817.0	1123.9	306.9	249.0	342.6	93.5	0.39	0.36	0.003
	including	1060.0	1117.0	57.0	323.1	340.5	17.4	0.88	0.86	0.003
	oxide	1195.0	1292.6	97.6	364.2	394.0	29.7	0.27	0.24	0.003
	including	1209.4	1238.3	28.9	368.6	377.4	8.8	0.39	0.38	0.007
	primary	1292.6	1875.4	582.8	394.0	571.6	177.6	0.45	0.04	0.010
	including	1462.7	1530.0	67.3	445.8	466.3	20.5	0.60	0.05	0.007
	and	1554.0	1594.0	40.0	473.7	485.9	12.2	0.62	0.04	0.010
	and	1764.0	1854.0	90.0	537.7	565.1	27.4	0.60	0.04	0.016

Notes:

1. Intervals are presented in core length and are drilled mostly vertically except where holes specifically support geotechnical programs.
2. Drill assays assume a mineralized cut-off grade of 0.1% CuT reflecting the potential for heap leaching of open pit material in the case of Oxide and Enriched or in the case of Primary material to provide typical average grades. Holes were typically terminated below the basement fault, however some infill holes at Parks/Salyer were terminated within primary mineralization.
3. Assay results are not capped. Intercepts are aggregated within geological confines of major mineral zones.
4. True widths are not known.